

INTER-SKIM

Flowable Polyester Glazing Putty

INTER-SKIM is a two part, flowable polyester glazing putty, ideal for final finishing over body filler, paint, pinholes, scratched and rust pits. Each bottle or pouch comes with a 1 oz. tube of hardener (#8802).



Superior Adhesion
Great Feather Edging
Easy To Sand
No Pin Holes

DIRECTIONS

1. Preparation: Clean surface with IES Super Clean to remove all dirt, waxes, grease, grime and any other contaminants. Sand surface with 180 grit sand paper and then wipe down again with IES Super Clean and allow to dry.
2. Mixing: Shake INTER-SKIM Polyester Putty well before using. Puncture inner seal and then dispense desired amount of INTER-SKIM Putty on a clean, non porous, mixing board. Knead the INTER-SKIM Hardener tube to insure contents are well mixed. Apply a ribbon of hardener to the INTER-SKIM at a ratio of 50:1 and mix thoroughly until color is uniform. Working time for this product is approximately 5 minutes.
3. Application: Using a plastic spreader, apply the mixed INTER-SKIM to the repair area. The fill should not exceed 1/8" in thickness. Allow to cure for approximately 15 to 20 minutes.
4. Finish: After curing, sand with 180 grit sand paper and then finish sanding with 220 to 400 grit prior to priming or sealing. Refer to paint manufacturers instructions before top coating.

NOTE: Do not apply INTER-SKIM Polyester Glazing Putty over the top of Methyl Methacrylate Adhesives

STORAGE

Product should be stored in a cool, dry location at a temperature between 50°F to 86°F (10°C to 30°C), temperature not to exceed 104°F (40°C). NOTE: Product may suffer from increased viscosity when stored at temperatures less than 60°F. Do not store in direct sunlight or near sources of ignition.

PRODUCT AVAILABLE

8801	32 Fl. Oz. (946 ml) Bottle	8/case
8803	20 Fl. Oz. (946 ml) Pouch	4/case
8802	1 Oz. Hardener Tube	1/case

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. International Epoxies & Sealers shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith.